

Arnitel[®] PM581

TPC-ET

Extrusion Grade, Heat Stabilized

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES		VALUE	
Melt volume-flow rate	4	cm ³ /10min	ISO 1133
Temperature	230	°C	ISO 1133
Load	2.16	kg	ISO 1133
MECHANICAL PROPERTIES		VALUE	
Shore D Hardness (3s)	53	—	ISO 868
Tensile modulus	250	MPa	ISO 527-1/-2
Stress at break	26	MPa	ISO 527-1/-2
Nominal strain at break	220	%	ISO 527-1/-2
Stress at 5% strain	9.5	MPa	ISO 527-1/-2
Stress at 10% strain	14	MPa	ISO 527-1/-2
Stress at 50% strain	18	MPa	ISO 527-1/-2
Stress at 100% strain	20	MPa	ISO 527-1/-2
Charpy notched impact strength (+23°C)	N	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	16	kJ/m ²	ISO 179/1eA
Izod notched impact strength (+23°C)	N	kJ/m ²	ISO 180/1A
Izod notched impact strength (-30°C)	25	kJ/m ²	ISO 180/1A
Flexural modulus	240	MPa	ISO 178
MECHANICAL PROPERTIES (DIE CUTTING)		VALUE	
Stress at break (normal)	43	MPa	ISO 527-1/-2
Stress at 100% strain (normal)	16	MPa	ISO 527-1/-2



Arnitel[®] PM581

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Tear strength (normal)	141	kN/m	ISO 34-1; Method B
Tear strength (parallel)	149	kN/m	ISO 34-1; Method B
Strain at break (normal)	710	%	ISO 527-1/-2

THERMAL PROPERTIES	VALUE		
Melting temperature (10°C/min)	218	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	100	°C	ISO 75-1/-2
Vicat softening temperature (50°C/h 50N)	80	°C	ISO 306
Vicat softening temperature (50°C/h 10N)	204	°C	ISO 306
Coeff. of linear therm. expansion (parallel)	1.1	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	1.1	E-4/°C	ISO 11359-1/-2

ELECTRICAL PROPERTIES	VALUE		
Relative permittivity (100Hz)	4.7	—	IEC 62631-2-1
Relative permittivity (1 MHz)	4.4	—	IEC 62631-2-1
Dissipation factor (100 Hz)	310	E-4	IEC 62631-2-1
Dissipation factor (1 MHz)	810	E-4	IEC 62631-2-1
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Electric strength	21	kV/mm	IEC 60243-1
Comparative tracking index	600	V	IEC 60112

OTHER PROPERTIES	VALUE		
Density	1240	kg/m³	ISO 1183
Water absorption	2.5	%	Sim. to ISO 62
Humidity absorption	0.4	%	Sim. to ISO 62

