

Arnitel[®] EM550

TPC-ET

Film Extrusion, Food Contact Quality

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES	VALUE		
Melt volume-flow rate	9	cm ³ /10min	ISO 1133
Temperature	230	°C	ISO 1133
Load	2.16	kg	ISO 1133
MECHANICAL PROPERTIES	VALUE		
Shore D Hardness (3s)	52	—	ISO 868
Tensile modulus	175	MPa	ISO 527-1/-2
Stress at break	25	MPa	ISO 527-1/-2
Nominal strain at break	360	%	ISO 527-1/-2
Stress at 5% strain	8	MPa	ISO 527-1/-2
Stress at 10% strain	12	MPa	ISO 527-1/-2
Stress at 50% strain	15	MPa	ISO 527-1/-2
Stress at 100% strain	16	MPa	ISO 527-1/-2
Charpy notched impact strength (+23°C)	N	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	25	kJ/m ²	ISO 179/1eA
Flexural modulus	180	MPa	ISO 178
Compression Set under constant strain at 70 °C	40	%	ISO 815
MECHANICAL PROPERTIES (DIE CUTTING)	VALUE		
Stress at break (normal)	41	MPa	ISO 527-1/-2
Tear strength (normal)	125	kN/m	ISO 34-1; Method B



Arnitel[®] EM550

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Tear strength (parallel)	134	kN/m	ISO 34-1; Method B
Strain at break (normal)	820	%	ISO 527-1/-2

THERMAL PROPERTIES	VALUE		
Melting temperature (10°C/min)	207	°C	ISO 11357-1/-3
Vicat softening temperature (50°C/h 50N)	90	°C	ISO 306
Coeff. of linear therm. expansion (parallel)	1.5	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	1.5	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	IEC 60695-11-10

ELECTRICAL PROPERTIES	VALUE		
Relative permittivity (100Hz)	4.4	—	IEC 62631-2-1
Relative permittivity (1 MHz)	4	—	IEC 62631-2-1
Dissipation factor (1 MHz)	400	E-4	IEC 62631-2-1
Volume resistivity	1E11	Ohm*m	IEC 62631-3-1
Electric strength	21	kV/mm	IEC 60243-1

OTHER PROPERTIES	VALUE		
Density	1200	kg/m³	ISO 1183
Water absorption	0.65	%	Sim. to ISO 62
Humidity absorption	0.2	%	Sim. to ISO 62

