

KOCETAL[®] GF302

Polyacetal + Glass Fiber, Reinforced, Injection Molding, Medium Viscosity

Properties	Measurement condition	Test Method	Unit	Typical value
Physical				
Density		ASTM D792	-	1.45
Melt Flow Index	190 °C, 2.16 kg	ASTM D1238	g/10min	13.0
Shrinkage		ASTM D955	%	0.8-1.4
Water Absorption	23 °C, H ₂ O, 24 hr	ASTM D570	%	0.2
Mechanical				
Tensile Strength at Yield (3.2mm)	5 mm/min	ASTM D638	MPa	95
Nominal Strain at Break(3.2mm)	5 mm/min	ASTM D638	%	-
Flexural Strength (3.2mm)	10 mm/min	ASTM D790	MPa	143
Flexural Modulus (3.2mm)	10 mm/min	ASTM D790	MPa	4,600
Izod Impact Strength (6.4mm)		ASTM D256		
(Notched)	23 °C		J/m	47
	-30 °C		J/m	-
Rockwell Hardness	M scale	ASTM D785	-	85
Thermal				
Melting Point	20 °C/min	ASTM D1525	°C	167
Heat Deflection Temperature	1.8 MPa	ASTM D648	°C	>160
Coefficient of linear expansion		ASTM D696	$\times 10^{-5}\text{cm/cm}\cdot^{\circ}\text{C}$	6
Flammability (0.8mm)		UL94	Class	HB
Electrical				
Dielectric Strength		IEC 60243	kV/mm	19
Volume Resistivity		IEC 60093	$\Omega\cdot\text{cm}$	1×10^{14}
Surface Resistivity		IEC 60093	Ω/sq	1×10^{16}

※ 1Mpa = 10.197162 Kgf/cm², 1J/m = 0.10197 Kgf·cm/cm, (Test specimen Thickness)



Processing Guide (Injection Molding)

Drying Temperature(℃)	80 ~ 90	(Dehumidifying Dryer)			
Drying Time(hr)	3 ~ 5				
Processing Moisture Contents(%)	≤ 0.1				
Cylinder Temperature(℃)	Nozzle	Front	Middle	Rear	
	190 ~ 210	190 ~ 210	180 ~ 200	170 ~ 190	
Mold Temperature(℃)	70 ~ 120				

