

PRODUCT INFORMATION

KOCETAL[®] KH702GN

Property	Test Method	Units	Value
Physical			
Melt Index	ASTM D1238	g/10min	42.0
Specific Gravity	ASTM D792	-	1.41
Shrinkage	ASTM D955	%	2.3
Water Absorption 23℃, Equilibrium 60%RH	ASTM D570	%	0.22
Thermal			
Melting Point	ASTM D1525	℃	166
Heat Deflection Temperature under Load	ASTM D648		
HDT/A 0.45 MPa (4.6 kg/cm ²)		℃	158
HDT/A 1.82 MPa (18.6 kg/cm ²)		℃	110
Vicat Softening Temperature	ASTM D1525	℃	162
Coeff. Of Linear Thermal Expansion	ASTM D696	× 10 ⁻⁵ cm/cm·℃	13
Flammability	UL 94		HB
Mechanical			
Tensile Strength 23℃	ASTM D638	MPa (kg/cm ²)	60 (600)
Tensile Elongation 23℃	ASTM D638	%	50
Flexural Strength 23℃	ASTM D790	MPa (kg/cm ²)	85 (870)
Flexural Modulus 23℃	ASTM D790	MPa (kg/cm ²)	2,500 (24,700)
Notched Izod Impact Strength 23℃	ASTM D256	J/m (kg cm/cm)	50 (5.1)
Rockwell Hardness M scale	ASTM D785	-	80
Electrical			
Surface Resistivity	ASTM D257	× 10 ¹⁶ Ω	1
Volume Resistivity	ASTM D257	× 10 ¹⁴ Ω cm	1
Dielectric Strength	ASTM D149	kV/mm	19
Dielectric Constant	ASTM D150	-	3.7
Dielectric Dissipation FactorConstant 10 ⁶ Hz	ASTM D150	-	0.006



KOLON PLASTICS, Inc.

