

PRODUCT INFORMATION

Low Odor Grade

KOCETAL[®] UR304LOBK

Kocetal UR304LOBK is impact strength modified grade suitable for fastener and switch.

And odor(low emission) of formaldehyde.

Property	Test Method	Units	Value
Physical			
Melt Index	ASTM D1238	g/10min	9.0
Specific Gravity	ASTM D792	-	1.36
Shrinkage	ASTM D955	%	1.7
Water Absorption 23 °C, Equilibrium 60%RH	ASTM D570	%	0.24
Thermal			
Melting Point	ASTM D1525	°C	166
Heat Deflection Temperature under Load	ASTM D648		
HDT/A 0.45 MPa (4.6 kg/cm ²)		°C	145
HDT/A 1.82 MPa (18.6 kg/cm ²)		°C	82
Vicat Softening Temperature	ASTM D1525	°C	
Coeff. Of Linear Thermal Expansion	ASTM D696	× 10 ⁻⁵ cm/cm·°C	13
Flammability	UL 94		HB
Mechanical			
Tensile Strength 23 °C	ASTM D638	MPa (kg/cm ²)	44 (450)
Tensile Elongation 23 °C	ASTM D638	%	120
Flexural Strength 23 °C	ASTM D790	MPa (kg/cm ²)	59 (600)
Flexural Modulus 23 °C	ASTM D790	MPa (kg/cm ²)	1,800 (1,8500)
Notched Izod Impact Strength 23 °C	ASTM D256	J/m (kg·cm/cm)	118 (12)
Rockwell Hardness M scale	ASTM D785	-	60
Electrical			
Surface Resistivity	ASTM D257	× 10 ¹⁶ Ω	1
Volume Resistivity	ASTM D257	× 10 ¹⁴ Ω·cm	1
Dielectric Strength	ASTM D149	kV/mm	19
Dielectric Constant	ASTM D150	-	3.7
Dielectric Dissipation FactorConstant 10 ⁶ Hz	ASTM D150	-	0.006

**KOLON PLASTICS, Inc.**