

KOCETAL[®] UR304LO

Polyacetal, Impact Modified, Low Emission, Injection molding, Medium-viscosity

Properties	Measurement condition	Test Method	Unit	Typical value
Physical				
Density		ISO 1183	g/cm ³	1.34
Melt Flow Index	190 °C, 2.16 kg	ISO 1133	g/10min	8.0
Melt Volume Rate	190 °C, 2.16 kg	ISO 1133	cm ³ /10min	6.8
Shrinkage		ISO 294-4	%	1.6-2.0
Water Absorption	23 °C, 50% RH	ISO 62	%	0.25
Mechanical				
Tensile Strength at Yield (4.0mm)	50 mm/min	ISO 527	MPa	42
Elongation at Break (4.0mm)	50 mm/min	ISO 527	%	>50
Strain at Yield, (4.0mm)	50 mm/min	ISO 527	%	20
Flexural Strength (4.0mm)	2 mm/min	ISO 178	MPa	58
Flexural Modulus (4.0mm)	2 mm/min	ISO 178	MPa	1,650
Charpy Impact Strength, (4.0mm)		ISO 179/1eA		
(Notched)	23 °C		kJ/m ²	19.0
	-30 °C		kJ/m ²	12.2
Rockwell Hardness	M scale	ISO 2039-2	-	80
Thermal				
Melting Point	20 °C/min	ISO 11357-1	°C	167
Heat Deflection Temperature	1.8 MPa	ISO 75	°C	72
Coefficient of linear expansion		ISO 11359	× E ⁻⁶ /K	-
Flammability (0.8mm)		UL94	Class	HB
Electrical				
Dielectric Strength		IEC 60243	kV/mm	-
Volume Resistivity		IEC 60093	Ω·cm	-
Surface Resistivity		IEC 60093	Ω	-
※ (Test specimen Thickness)				



Processing Guide (Injection Molding)

Drying Temperature(°C)	80 ~ 90	(Dehumidifying Dryer)			
Drying Time(hr)	3 ~ 5				
Limitation of Processing Temperature(°C)	200				
Processing Moisture Contents(%)	≤ 0.1				
Cylinder Temperature(°C)	Nozzle	Front	Middle	Rear	
	170 ~ 190	175 ~ 190	175 ~ 190	165 ~ 175	
Mold Temperature(°C)	60 ~ 80				

