

Product Information

Glass Fiber Reinforced Grade

KOPA[®] KN1 Series

KOPA[®] KN1 Series is the plastic material based on polyamide-6 that is a thermoplastic resin with excellent mechanical, thermal and electrical properties. KOPA[®] KN1 Series is widely used in the manufacture of automobile and industrial parts.

KOPA[®] KN133G15

Middle viscosity, G/F 15% reinforced Polyamide6 Compound resin

Properties	Test Method	Unit	Typical Value
------------	-------------	------	---------------

Physical

Specific Gravity	ISO 1183	-	1.24
Filler Contents	ISO 1172	%	15
Shrinkage	ISO 294	%	
Water Absorption	23°C, H ₂ O, 24hr	ISO 62	%

Mechanical

Tensile Strength	23°C	ISO 527	MPa	120
Tensile Elongation	23°C	ISO 527	%	2.9
Flexural Strength	23°C	ISO 178	MPa	185
Flexural Modulus	23°C	ISO 178	MPa	4,500
Notched Charpy Impact Strength	23°C	ISO 179/1eA	kJ/m ²	5.9
Rockwell Hardness		ISO 2039-1	R scale	

Thermal


Melting Point		ISO 11357-1	°C	225
Heat Deflection Temperature		ISO 75		
	0.45 MPa		°C	
	1.8 MPa		°C	190
Flammability(0.8mm)		UL94		



Electrical

Comparative Tracking Index(CTI)	IEC 60112	Volts	
Volume Resistivity	IEC 60093	Ohm·cm	
Surface Resistivity	IEC 60093	Ohm	

Processing Guide (Injection Molding)



	H1	H2	H3	H4
Cylinder Temperature(°C)	230	240	245	250
Mold Temperature(°C)	60~80			
Processing Moisture Contents(%)	≤0.05			
Pre-drying	Dehumidified Dryer, 80~100°C, 4~5hr			

