

PRODUCT INFORMATION

Hybrid Grade

KOPA[®] KN133HB40RRBL

Polyamide 6 Compound resin,

HYBRID, high thermal resistant, dimensionally stable

Property	Test Method	Units	Value
Physical			
Specific Gravity	ASTM D792	-	1.46
Shrinkage	ASTM D955	%	0.1-0.3
Water Absorption 23℃, Equilibrium 60%RH	ASTM D570	%	0.4
Thermal			
Melting Point	ASTM D3418	℃	220
Heat Deflection Temperature under Load	ASTM D648		
HDT/A 0.45 MPa (4.6 kg/cm ²)		℃	210
HDT/A 1.82 MPa (18.6 kg/cm ²)		℃	203
Coeff. Of Linear Thermal Expansion	ASTM D696	× 10 ⁻⁴ cm/cm·℃	0.4
Flammability	UL 94		HB
Mechanical			
Tensile Strength 23℃	ASTM D638	MPa (kg/cm ²)	128(1300)
Tensile Elongation 23℃	ASTM D638	%	7
Flexural Strength 23℃	ASTM D790	MPa (kg/cm ²)	216(2200)
Flexural Modulus 23℃	ASTM D790	MPa (kg/cm ²)	7355(75000)
Notched Izod Impact Strength 23℃	ASTM D256	J/m (kg·cm/cm)	59(6)
Rockwell Hardness R scale	ASTM D785	g/cc	120
Electrical			
Arc Resistance	ASTM D495	sec	136
Dielectric Constant	ASTM D150	10 ⁶ Hz	3.5
Dielectric Strength	ASTM D149	KV/mm	22

**KOLON PLASTICS, Inc.**