

KOPA® KN133G50

Injection Molding, PA6+GF50%, Medium viscosity

Application

General

Properties	Measurement condition	Test Method	Unit	Typical value
Physical				
Density		ASTM D792	—	1.56
Shrinkage		ASTM D955	%	0.1 ~ 0.4
Water Absorption	23℃, H ₂ O, 24hr	ASTM D570	%	0.9
Mechanical				
Tensile Strength at Break (3.2mm)	5 mm/min	ASTM D638	MPa	210
Elongation at Break (3.2mm)	5 mm/min	ASTM D638	%	—
Flexural Strength (3.2mm)	5 mm/min	ASTM D790	MPa	340
Flexural Modulus (3.2mm)	5 mm/min	ASTM D790	MPa	13000
Izod Impact Strength (6.4mm) (Notched)		ASTM D256		
	23 ℃		J/m	230
	-30 ℃		J/m	—
Rockwell Hardness	R scale	ASTM D785	—	120
Thermal				
Melting Point	20 ℃/min	ASTM D1525	℃	225
Heat Deflection Temperature	1.8 MPa	ASTM D648	℃	210
Flammability (0.8mm)		UL94	Class	HB

※ 1Mpa = 10.197162 Kgf/cm², 1J/m = 0.10197 Kgf · cm/cm, (Test specimen Thickness)



Processing Guide (Injection Molding)

Drying Temperature(℃)	80 ~ 90			
	(Dehumidifying Dryer)			
Drying Time(hr)	3~5			
Processing Moisture Contents(%)	≤ 0.1			
Cylinder Temperature(℃)	Nozzle	Front	Middle	Rear
	260~290	260~290	250~280	240~270
Mold Temperature(℃)	60~100			

