

Product Information

Glass Fiber & Mineral Reinforced Grade

KOPA[®] KN1 Series

KOPA[®] KN1 Series is the plastic material based on polyamide-6 that is a thermoplastic resin with excellent mechanical, thermal and electrical properties. KOPA[®] KN1 Series is widely used in the manufacture of automobile and industrial parts.

KOPA[®] KN133HB40GR

Hybrid, High thermal resistant, Dimensionally stable, Gray color

Properties	Test Method	Unit	Typical Value
------------	-------------	------	---------------

Physical

Specific Gravity	ISO 1183	-	1.44
Filler Contents	ISO 1172	%	40
Shrinkage	ISO 294	%	
Water Absorption	ISO 62	%	
23°C, H ₂ O, 24hr			

Mechanical

Tensile Strength	23°C	ISO 527	MPa	115
Tensile Elongation	23°C	ISO 527	%	3
Flexural Strength	23°C	ISO 178	MPa	160
Flexural Modulus	23°C	ISO 178	MPa	6,500
Notched Charpy Impact Strength	23°C	ISO 179/1eA	kJ/m ²	4
Rockwell Hardness		ISO 2039-1	R scale	


Thermal

Melting Point		ISO 11357-1	°C	220
Heat Deflection Temperature		ISO 75		
	0.45 MPa		°C	
	1.8 MPa		°C	185
Flammability(0.8mm)		UL94		

Electrical

Comparative Tracking Index(CTI)	IEC 60112	Volts	
Volume Resistivity	IEC 60093	Ohm·cm	
Surface Resistivity	IEC 60093	Ohm	

Processing Guide (Injection Molding)



	H1	H2	H3	H4
Cylinder Temperature(°C)	230	255	260	265
Mold Temperature(°C)	60~80			
Processing Moisture Contents(%)	≤0.05			
Pre-drying	Dehumidified Dryer, 80~100°C, 4~5hr			

