

PRODUCT INFORMATION

Glass Fiber Reinforced Grade

KOPA[®] KN333G30BL1

Polyamide 66 Compound resin,
G/F 30% reinforced, black

Property	Test Method	Units	Value
Physical			
Specific Gravity	ASTM D792	-	1.36
Shrinkage	ASTM D955	%	0.28-0.35
Water Absorption 23℃, Equilibrium 60%RH	ASTM D570	%	0.4
Thermal			
Melting Point	ASTM D3418	℃	255
Heat Deflection Temperature under Load	ASTM D648		
HDT/A 0.45 MPa (4.6 kg/cm ²)		℃	250
HDT/A 1.82 MPa (18.6 kg/cm ²)		℃	247
Coeff. Of Linear Thermal Expansion	ASTM D696	× 10 ⁻⁴ cm/cm·℃	0.2
Flammability	UL 94		HB
Mechanical			
Tensile Strength 23℃	ASTM D638	MPa (kg/cm ²)	186(1900)
Tensile Elongation 23℃	ASTM D638	%	6
Flexural Strength 23℃	ASTM D790	MPa (kg/cm ²)	275(2800)
Flexural Modulus 23℃	ASTM D790	MPa (kg/cm ²)	7840(80000)
Notched Izod Impact Strength 23℃	ASTM D256	J/m (kg·cm/cm)	108(11)
Rockwell Hardness	ASTM D785	R scale	121
Electrical			
Arc Resistance	ASTM D495	sec	135
Dielectric Constant	ASTM D150	10 ⁶ Hz	3.6
Dielectric Strength	ASTM D149	KV/mm	21

**KOLON PLASTICS, Inc.**