

PRODUCT INFORMATION

Flame Retardant Grade

KOPA[®] KN3321V0BL

Polyamide 66 Compound resin,

Middle viscosity, Halogen free, Impact -resistant, Black color

Property	Test Method	Units	Value
Physical			
Specific Gravity	ASTM D792	-	1.29
Shrinkage	ASTM D955	%	1.3-1.6
Water Absorption 23℃, Equilibrium 60%RH	ASTM D570	%	0.6
Thermal			
Melting Point	ASTM D3418	℃	255
Heat Deflection Temperature under Load	ASTM D648		
HDT/A 0.45 MPa (4.6 kg/cm ²)		℃	235
HDT/A 1.82 MPa (18.6 kg/cm ²)		℃	105
Coeff. Of Linear Thermal Expansion	ASTM D696	× 10 ⁻⁴ cm/cm·℃	0.7
Flammability	UL 94		V0
Mechanical			
Tensile Strength 23℃	ASTM D638	MPa (kg/cm ²)	86(890)
Tensile Elongation 23℃	ASTM D638	%	13
Flexural Strength 23℃	ASTM D790	MPa (kg/cm ²)	136(1400)
Flexural Modulus 23℃	ASTM D790	MPa (kg/cm ²)	3422(34900)
Notched Izod Impact Strength 23℃	ASTM D256	J/m (kg·cm/cm)	45(4)
Rockwell Hardness R scale	ASTM D785	g/cc	120
Electrical			
Arc Resistance	ASTM D495	sec	125
Dielectric Constant	ASTM D150	10 ⁶ Hz	3.4
Dielectric Strength	ASTM D149	KV/mm	20

**KOLON PLASTICS, Inc.**