

PRODUCT INFORMATION

Impact Resistant Grade

KOPA[®] KN333HI4BL

Polyamide 66 Compound resin,
Middle viscosity, Impact -resistant

Property	Test Method	Units	Value
Physical			
Specific Gravity	ASTM D792	-	1.08
Shrinkage	ASTM D955	%	1.7-2.0
Water Absorption 23℃, Equilibrium 60%RH	ASTM D570	%	0.9
Thermal			
Melting Point	ASTM D3418	℃	255
Heat Deflection Temperature under Load	ASTM D648		
HDT/A 0.45 MPa (4.6 kg/cm ²)		℃	200
HDT/A 1.82 MPa (18.6 kg/cm ²)		℃	70
Coeff. Of Linear Thermal Expansion	ASTM D696	× 10 ⁻⁴ cm/cm·℃	0.6
Flammability	UL 94		HB
Mechanical			
Tensile Strength 23℃	ASTM D638	MPa (kg/cm ²)	54(550)
Tensile Elongation 23℃	ASTM D638	%	75
Flexural Strength 23℃	ASTM D790	MPa (kg/cm ²)	68(690)
Flexural Modulus 23℃	ASTM D790	MPa (kg/cm ²)	1520(15500)
Notched Izod Impact Strength 23℃	ASTM D256	J/m (kg·cm/cm)	NB
Rockwell Hardness R scale	ASTM D785	g/cc	110
Electrical			
Arc Resistance	ASTM D495	sec	125
Dielectric Constant	ASTM D150	10 ⁶ Hz	3.1
Dielectric Strength	ASTM D149	KV/mm	20

**KOLON PLASTICS, Inc.**