

PRODUCT INFORMATION

Mineral Reinforced Grade

KOPA[®] KN333MT30BLPolyamide 66 Compound resin,
MF reinforced

Property	Test Method	Units	Value
Physical			
Specific Gravity	ASTM D792	-	1.34
Shrinkage	ASTM D955	%	0.5-0.8
Water Absorption 23 °C, Equilibrium 60%RH	ASTM D570	%	0.3
Thermal			
Melting Point	ASTM D3418	°C	255
Heat Deflection Temperature under Load	ASTM D648		
HDT/A 0.45 MPa (4.6 kg/cm ²)		°C	240
HDT/A 1.82 MPa (18.6 kg/cm ²)		°C	230
Coeff. Of Linear Thermal Expansion	ASTM D696	× 10 ⁻⁴ cm/cm·°C	0.2
Flammability	UL 94		HB
Mechanical			
Tensile Strength 23 °C	ASTM D638	MPa (kg/cm ²)	74(750)
Tensile Elongation 23 °C	ASTM D638	%	8
Flexural Strength 23 °C	ASTM D790	MPa (kg/cm ²)	118(1200)
Flexural Modulus 23 °C	ASTM D790	MPa (kg/cm ²)	4119(42000)
Notched Izod Impact Strength 23 °C	ASTM D256	J/m (kg cm/cm)	49(5)
Rockwell Hardness R scale	ASTM D785	g/cc	125
Electrical			
Arc Resistance	ASTM D495	sec	133
Dielectric Constant	ASTM D150	10 ⁶ Hz	3.4
Dielectric Strength	ASTM D149	KV/mm	20

**KOLON PLASTICS, Inc.**