

PRODUCT INFORMATION

Glass Fiber Reinforced Grade

KOPET[®] KP133G15GN

Polyester compound resin,

Dimensionally stable, high elastic, high flow

Property	Test Method	Units	Value
Physical			
Specific Gravity	ASTM D792	-	1.45
Shrinkage	ASTM D955	%	0.2-0.5
Water Absorption 23℃, Equilibrium 60%RH	ASTM D570	%	0.1
Thermal			
Melting Point	ASTM D3418	℃	255
Heat Deflection Temperature under Load	ASTM D648		
HDT/A 0.45 MPa (4.6 kg/cm ²)		℃	235
HDT/A 1.82 MPa (18.6 kg/cm ²)		℃	185
Coeff. Of Linear Thermal Expansion	ASTM D696	× 10 ⁻⁴ cm/cm·℃	0.4
Flammability	UL 94		HB
Mechanical			
Tensile Strength 23℃	ASTM D638	MPa (kg/cm ²)	98(1000)
Tensile Elongation 23℃	ASTM D638	%	5.5
Flexural Strength 23℃	ASTM D790	MPa (kg/cm ²)	157(1600)
Flexural Modulus 23℃	ASTM D790	MPa (kg/cm ²)	5688(58000)
Notched Izod Impact Strength 23℃	ASTM D256	J/m (kg·cm/cm)	35(3.6)
Rockwell Hardness R scale	ASTM D785	g/cc	110
Electrical			
Arc Resistance	ASTM D495	sec	119
Dielectric Constant	ASTM D150	10 ⁶ Hz	3.7
Dielectric Strength	ASTM D149	KV/mm	19

**KOLON PLASTICS, Inc.**