

General Grade

SPESIN[®]

PBT Compound resin,

Property		Test Method	Units	Value
Physical				
Specific Gravity		ASTM D792	-	1.31
Shrinkage		ASTM D955	%	1.8-2.3
Water Absorption	23°C, Equilibrium 60%RH	ASTM D570	%	0.07
Thermal				
Melting Point		ASTM D3418	°C	224
Heat Deflection Temperature under Load		ASTM D648		
	HDT/A 0.45 MPa (4.6 kg/cm ²)		°C	166
	HDT/A 1.82 MPa (18.6 kg/cm ²)		°C	59
Coeff. Of Linear Thermal Expansion		ASTM D696	× 10 ⁻⁴ cm/cm·°C	0.8
Flammability		UL 94		HB
Mechanical				
Tensile Strength	23°C	ASTM D638	MPa (kg/cm ²)	57(580)
Tensile Elongation	23°C	ASTM D638	%	75
Flexural Strength	23°C	ASTM D790	MPa (kg/cm ²)	93(950)
Flexural Modulus	23°C	ASTM D790	MPa (kg/cm ²)	2452(25000)
Notched Izod Impact Strength	23°C	ASTM D256	J/m (kg ·cm/cm)	49(5)
Rockwell Hardness	R scale	ASTM D785	g/cc	118
Electrical				
Arc Resistance		ASTM D495	sec	120
Dielectric Constant		ASTM D150	10 ⁶ Hz	3.1
Dielectric Strength		ASTM D149	KV/mm	28

