

PRODUCT INFORMATION

Glass Fiber Reinforced Grade

SPESIN[®] KP213G15SI

PBT Compound resin,
G/F 15%, high toughness, excellent surface

Property	Test Method	Units	Value
Physical			
Specific Gravity	ASTM D792	-	1.41
Shrinkage	ASTM D955	%	0.7-1.1
Water Absorption 23℃, Equilibrium 60%RH	ASTM D570	%	0.05
Thermal			
Melting Point	ASTM D3418	℃	224
Heat Deflection Temperature under Load	ASTM D648		
HDT/A 0.45 MPa (4.6 kg/cm ²)		℃	220
HDT/A 1.82 MPa (18.6 kg/cm ²)		℃	205
Coeff. Of Linear Thermal Expansion	ASTM D696	× 10 ⁻⁴ cm/cm·℃	0.4
Flammability	UL 94		HB
Mechanical			
Tensile Strength 23℃	ASTM D638	MPa (kg/cm ²)	100(1020)
Tensile Elongation 23℃	ASTM D638	%	7
Flexural Strength 23℃	ASTM D790	MPa (kg/cm ²)	173(1765)
Flexural Modulus 23℃	ASTM D790	MPa (kg/cm ²)	5443(55500)
Notched Izod Impact Strength 23℃	ASTM D256	J/m (kg cm/cm)	49(5)
Rockwell Hardness R scale	ASTM D785	g/cc	120
Electrical			
Arc Resistance	ASTM D495	sec	120
Dielectric Constant	ASTM D150	10 ⁶ Hz	3.2
Dielectric Strength	ASTM D149	KV/mm	30

**KOLON PLASTICS, Inc.**