

Iuplace™ AV90

Mitsubishi Engineering-Plastics Corp - Polyphenylene Ether + PS

General Information			
Product Description			
V-1			
General			
Features	• Flame Retardant		
Uses	• Automotive Applications • Automotive Electronics	• Electrical/Electronic Applications • General Purpose	
ASTM & ISO Properties ¹			
Physical	Nominal Value	Unit	Test Method
Density	1.08	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (300°C/2.16 kg)	2.8	cm³/10min	ISO 1133
Molding Shrinkage			Internal Method
Across Flow : 3.20 mm	0.50 to 0.70	%	
Flow : 3.20 mm	0.50 to 0.70	%	
Water Absorption (Saturation, 23°C)	0.070	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2600	MPa	ISO 527-1/1
Tensile Stress (Yield)	70.0	MPa	ISO 527-2/50
Tensile Strain			ISO 527-2/50
Yield	5.6	%	
Break	30	%	
Flexural Modulus ²	2600	MPa	ISO 178
Flexural Stress ²	103	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	9.0	kJ/m²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	160	°C	ISO 75-2/B
1.8 MPa, Unannealed	145	°C	ISO 75-2/A
CLTE			ISO 11359-2
Flow	6.0E-5	cm/cm/°C	
Transverse	6.3E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	2.0E+15	ohms	IEC 60093
Volume Resistivity	3.0E+16	ohms·cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.75 mm)	V-1		UL 94



Iupiace™ AV90

Mitsubishi Engineering-Plastics Corp - Polyphenylene Ether + PS

Processing Information

Injection	Nominal Value	Unit
Drying Temperature - Hot Air Dryer	100 to 120	°C
Drying Time - Hot Air Dryer	2.0 to 4.0	hr
Rear Temperature	250 to 280	°C
Middle Temperature	270 to 300	°C
Front Temperature	270 to 300	°C
Nozzle Temperature	270 to 300	°C
Mold Temperature	80 to 110	°C
Injection Pressure	20.0 to 150	MPa
Injection Rate	Moderate	
Screw Speed	60 to 150	rpm

