

Iuplace™ AH70

Mitsubishi Engineering-Plastics Corp - Polyphenylene Ether + PS

General Information			
Product Description			
HB			
General			
Uses	- Automotive Applications - Automotive Electronics	- Electrical/Electronic Applications - General Purpose	
ASTM & ISO Properties ¹			
Physical	Nominal Value	Unit	Test Method
Density	1.07	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (300°C/2.16 kg)	5.9	cm ³ /10min	ISO 1133
Molding Shrinkage			Internal Method
Across Flow : 3.20 mm	0.50 to 0.70	%	
Flow : 3.20 mm	0.50 to 0.70	%	
Water Absorption (Saturation, 23°C)	0.070	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2500	MPa	ISO 527-1/1
Tensile Stress (Yield)	58.0	MPa	ISO 527-2/50
Tensile Strain			ISO 527-2/50
Yield	5.4	%	
Break	24	%	
Flexural Modulus ²	2500	MPa	ISO 178
Flexural Stress ²	102	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	20	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	140	°C	ISO 75-2/B
1.8 MPa, Unannealed	125	°C	ISO 75-2/A
CLTE			ISO 11359-2
Flow	6.6E-5	cm/cm/°C	
Transverse	6.9E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	2.0E+15	ohms	IEC 60093
Volume Resistivity	3.0E+16	ohms·cm	IEC 60093
Electric Strength			IEC 60243-1
1.00 mm	44	kV/mm	
3.00 mm	> 65	kV/mm	



Iupiace™ AH70

Mitsubishi Engineering-Plastics Corp - Polyphenylene Ether + PS

Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.75 mm)	HB		UL 94

Processing Information			
Injection	Nominal Value	Unit	
Drying Temperature - Hot Air Dryer	90 to 100	°C	
Drying Time - Hot Air Dryer	2.0 to 4.0	hr	
Rear Temperature	240 to 270	°C	
Middle Temperature	260 to 290	°C	
Front Temperature	270 to 290	°C	
Nozzle Temperature	260 to 290	°C	
Mold Temperature	80 to 110	°C	
Injection Pressure	20.0 to 150	MPa	
Injection Rate	Moderate		
Screw Speed	60 to 150	rpm	

