

Iuplace™ LN30

Mitsubishi Engineering-Plastics Corp - Polyphenylene Ether + PS

General Information			
Product Description			
V-0			
General			
Features	• Flame Retardant		
Uses	• Automotive Applications • Automotive Electronics	• Electrical/Electronic Applications • General Purpose	
ASTM & ISO Properties ¹			
Physical	Nominal Value	Unit	Test Method
Density	1.10	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (300°C/2.16 kg)	16	cm³/10min	ISO 1133
Molding Shrinkage			Internal Method
Across Flow : 3.20 mm	0.50 to 0.70	%	
Flow : 3.20 mm	0.50 to 0.70	%	
Water Absorption (Saturation, 23°C)	0.070	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	55.0	MPa	ISO 527-2/50
Tensile Strain (Break)	25	%	ISO 527-2/50
Flexural Modulus ²	2400	MPa	ISO 178
Flexural Stress ²	90.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	13	kJ/m²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	105	°C	ISO 75-2/B
1.8 MPa, Unannealed	90.0	°C	ISO 75-2/A
CLTE			ISO 11359-2
Flow	5.5E-5	cm/cm/°C	
Transverse	5.8E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	2.0E+15	ohms	IEC 60093
Volume Resistivity	3.0E+16	ohms·cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.75 mm)	V-0		UL 94
Processing Information			
Injection	Nominal Value	Unit	
Drying Temperature - Hot Air Dryer	70 to 80	°C	
Drying Time - Hot Air Dryer	2.0 to 4.0	hr	



Iupiace™ LN30

Mitsubishi Engineering-Plastics Corp - Polyphenylene Ether + PS

Injection	Nominal Value	Unit
Rear Temperature	230 to 260	°C
Middle Temperature	250 to 280	°C
Front Temperature	250 to 280	°C
Nozzle Temperature	240 to 260	°C
Mold Temperature	50 to 90	°C
Injection Pressure	20.0 to 150	MPa
Injection Rate	Moderate	
Screw Speed	60 to 150	rpm

