

General Information				
Product Description				
Un-reinforced PPE/PA66 alloy; Flow, Super-High; Anti-vibration				
General				
Features	• High Flow	• Vibration Damping		
Uses	• Automotive Applications • Automotive Electronics	• Electrical/Electronic Applications • General Purpose		
ASTM & ISO Properties ¹				
Physical	Dry	Conditioned	Unit	Test Method
Density	1.13	--	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR)				ISO 1133
280°C/5.0 kg	90	--	cm³/10min	
Molding Shrinkage				Internal Method
Across Flow : 3.20 mm	1.1 to 1.3	--	%	
Flow : 3.20 mm	1.1 to 1.3	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	2600	1500	MPa	ISO 527-1/1
Tensile Stress (Yield)	60.0	45.0	MPa	ISO 527-2/50
Tensile Strain				ISO 527-2/50
Yield	4.8	19	%	
Break	47	88	%	
Flexural Modulus ²	2400	1500	MPa	ISO 178
Flexural Stress ²	90.0	60.0	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179
23°C	20	62	kJ/m²	
Charpy Unnotched Impact Strength				ISO 179
23°C	No Break	No Break		
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				
0.45 MPa, Unannealed	165	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	70.0	--	°C	ISO 75-2/A
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	7.0E+14	--	ohms	IEC 60093
Volume Resistivity	2.0E+15	--	ohms·cm	IEC 60093
Electric Strength				IEC 60243-1
1.00 mm	33	--	kV/mm	
3.00 mm	18	--	kV/mm	



LEMALLOY™ C82HL

Mitsubishi Engineering-Plastics Corp - Polyphenylene Ether + PA 66

Electrical	Dry	Conditioned	Unit	Test Method
Dielectric Constant				IEC 60250
1 MHz	3.20	--		
100 MHz	3.40	--		
Dissipation Factor				IEC 60250
1 MHz	0.012	--		
100 MHz	5.0E-3	--		

Additional Information

Conditioned	Conditioned to 50% RH
-------------	-----------------------

Processing Information

Injection	Dry	Unit
Drying Temperature - Hot Air Dryer	110 to 120	°C
Drying Time - Hot Air Dryer	2.0 to 4.0	hr
Rear Temperature	240 to 260	°C
Middle Temperature	250 to 280	°C
Front Temperature	250 to 280	°C
Nozzle Temperature	250 to 280	°C
Mold Temperature	60 to 100	°C
Injection Pressure	20.0 to 150	MPa
Injection Rate	Moderate	
Screw Speed	60 to 150	rpm

