

General Information

Product Description

GF-reinforced (15%) / V-0 (0.75mm), Light stabilized, High reflectivity

General

Filler / Reinforcement	• Glass Fiber, 15% Filler by Weight	
Features	• High Reflectivity	• Light Stabilized
Uses	• Automotive Applications	• Electrical/Electronic Applications
	• Automotive Electronics	• General Purpose
Appearance	• White	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.68	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (250°C/5.0 kg)	43	cm ³ /10min	ISO 1133
Molding Shrinkage			Internal Method
Across Flow : 2.00 mm	1.4	%	
Flow : 2.00 mm	0.80	%	
Water Absorption (Saturation, 23°C)	0.080	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6900	MPa	ISO 527-1/1
Tensile Stress (Break)	80.0	MPa	ISO 527-2/5
Tensile Strain (Break)	2.0	%	ISO 527-2/5
Flexural Modulus ²	6700	MPa	ISO 178
Flexural Stress ²	126	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	4.0	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	215	°C	
1.8 MPa, Unannealed	195	°C	
Melting Temperature	224	°C	ISO 11357-3
RTI Elec (0.75 mm)	140	°C	UL 746B
RTI Imp (0.75 mm)	125	°C	UL 746B
RTI Str (0.75 mm)	140	°C	UL 746B
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index (CTI)	PLC 2		UL 746A
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.75 mm)	V-0		UL 94



NOVADURAN™ 5010GN8-15LTi3

Mitsubishi Engineering-Plastics Corp - Polybutylene Terephthalate

Processing Information		
Injection	Nominal Value	Unit
Drying Temperature - Hot Air Dryer	120	°C
Drying Time - Hot Air Dryer	5.0 to 8.0	hr
Rear Temperature	250 to 270	°C
Middle Temperature	250 to 270	°C
Front Temperature	250 to 270	°C
Nozzle Temperature	270	°C
Mold Temperature	60 to 100	°C
Injection Pressure	20.0 to 150	MPa
Injection Rate	Moderate-Fast	
Screw Speed	80 to 150	rpm

