

NOVADURAN™ 5510FBGN 6

Mitsubishi Engineering-Plastics Corp - Polybutylene Terephthalate

General Information

Product Description

GF+Filler-reinforced / V-0 (1.6mm), V-2 (0.4mm)

General

Filler / Reinforcement	• Filler	
Features	• Flame Retardant	
Uses	• Automotive Applications • Automotive Electronics	• Electrical/Electronic Applications • General Purpose

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.98	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (250°C/5.0 kg)	37	cm ³ /10min	ISO 1133
Molding Shrinkage			Internal Method
Across Flow : 2.00 mm	1.0	%	
Flow : 2.00 mm	0.40	%	
Water Absorption (Saturation, 23°C)	0.070	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	110	MPa	ISO 527-2/5
Tensile Strain (Break)	2.0	%	ISO 527-2/5
Flexural Modulus ²	10800	MPa	ISO 178
Flexural Stress ²	170	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	8.0	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	224	°C	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index (CTI)	PLC 2		UL 746A
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.40 mm, Black, Natural color	V-2		
1.6 mm, Black, Natural color	V-0		

Processing Information

Injection	Nominal Value	Unit
Drying Temperature - Hot Air Dryer	120	°C
Drying Time - Hot Air Dryer	5.0 to 8.0	hr
Rear Temperature	250 to 270	°C
Middle Temperature	250 to 270	°C
Front Temperature	250 to 270	°C



NOVADURAN™ 5510FBGN 6

Mitsubishi Engineering-Plastics Corp - Polybutylene Terephthalate

Injection	Nominal Value	Unit
Nozzle Temperature	270	°C
Mold Temperature	60 to 100	°C
Injection Pressure	20.0 to 150	MPa
Injection Rate	Moderate-Fast	
Screw Speed	80 to 120	rpm

