

General Information			
Product Description			
PBT alloy GF-reinforced / HB equivalent per in-house testing, Rigidity High, GF 55%			
General			
Filler / Reinforcement	• Glass Fiber, 55% Filler by Weight		
Features	• High Rigidity		
Uses	• Automotive Applications • Electrical/Electronic Applications • Automotive Electronics • General Purpose		
ASTM & ISO Properties ¹			
Physical	Nominal Value	Unit	Test Method
Density	1.81	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (265°C/5.0 kg)	9.0	cm³/10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	0.60	%	
Flow	0.20	%	
Water Absorption (Saturation, 23°C)	0.070	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	21100	MPa	ISO 527-1/1
Tensile Stress (Break)	171	MPa	ISO 527-2/5
Tensile Strain (Break)	2.0	%	ISO 527-2/5
Flexural Modulus ²	17900	MPa	ISO 178
Flexural Stress ²	260	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	10	kJ/m²	ISO 179
Charpy Unnotched Impact Strength (23°C)	60	kJ/m²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Annealed	> 220	°C	ISO 75-2/B
1.8 MPa, Annealed	210	°C	ISO 75-2/A
Melting Temperature	255	°C	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	5.0E+16	ohms	IEC 60093
Volume Resistivity	2.0E+16	ohms·cm	IEC 60093
Dielectric Constant (1 MHz)	3.40		IEC 60250
Dissipation Factor (1 MHz)	0.016		IEC 60250
Processing Information			
Injection	Nominal Value	Unit	
Drying Temperature - Hot Air Dryer	120	°C	



NOVADURAN™ 5308G55

Mitsubishi Engineering-Plastics Corp - Polybutylene Terephthalate + PET

Injection	Nominal Value	Unit
Drying Time - Hot Air Dryer	5.0 to 8.0	hr
Rear Temperature	250 to 270	°C
Middle Temperature	250 to 270	°C
Front Temperature	250 to 270	°C
Nozzle Temperature	270	°C
Mold Temperature	60 to 100	°C
Injection Pressure	20.0 to 150	MPa
Injection Rate	Moderate-Fast	
Screw Speed	80 to 120	rpm

