

Iupilon™ CFH2030

Mitsubishi Engineering-Plastics Corp - Polycarbonate

General Information			
Product Description			
Carbon Fiber Reinforced, CF30%			
General			
Filler / Reinforcement	• Carbon Fiber, 30% Filler by Weight		
Features	• High Rigidity • High Stiffness		
Uses	• General Purpose		
ASTM & ISO Properties ¹			
Physical	Nominal Value	Unit	Test Method
Density	1.31	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	3.9	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	3.6	cm³/10min	ISO 1133
Molding Shrinkage			Internal Method
Across Flow	0.20 to 0.40	%	
Flow	0.010 to 0.15	%	
Water Absorption (24 hr, 23°C)	0.070	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	17200	MPa	ISO 527-1/1
Tensile Stress (Break)	155	MPa	ISO 527-2/5
Tensile Strain (Break)	2.2	%	ISO 527-2/5
Flexural Modulus ²	16200	MPa	ISO 178
Flexural Stress ²	210	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	9.0	kJ/m²	ISO 179
Charpy Unnotched Impact Strength (23°C)	40	kJ/m²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	152	°C	ISO 75-2/B
1.8 MPa, Unannealed	146	°C	ISO 75-2/A
CLTE			ISO 11359-2
Flow	6.0E-6	cm/cm/°C	
Transverse	5.7E-5	cm/cm/°C	
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.40 mm)	HB		UL 94



Iupilon™ CFH2030
Mitsubishi Engineering-Plastics Corp - Polycarbonate

Processing Information		
Injection	Nominal Value	Unit
Drying Temperature - Hot Air Dryer	120	°C
Drying Time - Hot Air Dryer	4.0 to 8.0	hr
Rear Temperature	290 to 310	°C
Middle Temperature	290 to 310	°C
Front Temperature	290 to 310	°C
Nozzle Temperature	290 to 310	°C
Mold Temperature	80 to 120	°C

