

Iupilon™ DSH3002R 7011A

Mitsubishi Engineering-Plastics Corp - Polycarbonate

General Information			
Product Description			
Light Diffusion, Low class			
General			
Features	• Low Light Diffusion		
Uses	• Displays • Lighting Applications • LEDs • Lighting Diffusers		
ASTM & ISO Properties ¹			
Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	14	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	14	cm³/10min	ISO 1133
Molding Shrinkage			Internal Method
Across Flow	0.50 to 0.70	%	
Flow	0.50 to 0.70	%	
Water Absorption (24 hr, 23°C)	0.24	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2500	MPa	ISO 527-1/1
Tensile Stress (Yield)	59.0	MPa	ISO 527-2/50
Tensile Strain (Yield)	6.5	%	ISO 527-2/50
Nominal Tensile Strain at Break	120	%	ISO 527-2/50
Flexural Modulus ²	2300	MPa	ISO 178
Flexural Stress ²	89.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	9.0	kJ/m²	ISO 179
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	136	°C	ISO 75-2/B
1.8 MPa, Unannealed	124	°C	ISO 75-2/A
CLTE			ISO 11359-2
Flow	6.5E-5	cm/cm/°C	
Transverse	6.6E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	6.0E+15	ohms	IEC 60093
Volume Resistivity	3.0E+16	ohms·cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.75 mm)	HB		UL 94



Iupilon™ DSH3002R 7011A
Mitsubishi Engineering-Plastics Corp - Polycarbonate

Processing Information		
Injection	Nominal Value	Unit
Drying Temperature - Hot Air Dryer	120	°C
Drying Time - Hot Air Dryer	4.0 to 8.0	hr
Rear Temperature	270 to 300	°C
Middle Temperature	270 to 300	°C
Front Temperature	270 to 300	°C
Nozzle Temperature	270 to 300	°C
Mold Temperature	70 to 100	°C

