

Iupilon™ EGN2030KR

Mitsubishi Engineering-Plastics Corp - Polycarbonate

General Information			
Product Description			
GF Reinforced (30%); Flame Retardant, Non Br & Non P; High Flow			
General			
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight		
Additive	• Flame Retardant		
Features	• Bromine Free • Flame Retardant	• High Flow • Low (to None) Phosphorus Content	
Uses	• General Purpose		
ASTM & ISO Properties ¹			
Physical	Nominal Value	Unit	Test Method
Density	1.43	g/cm³	ISO 1183
Molding Shrinkage			Internal Method
Across Flow	0.20 to 0.40	%	
Flow	0.10 to 0.30	%	
Water Absorption (Saturation, 23°C)	0.090	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	100	MPa	ISO 527-2/5
Tensile Strain (Break)	2.3	%	ISO 527-2/5
Flexural Modulus ²	8000	MPa	ISO 178
Flexural Stress ²	153	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	9.0	kJ/m²	ISO 179
Charpy Unnotched Impact Strength (23°C)	32	kJ/m²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	144	°C	ISO 75-2/B
1.8 MPa, Unannealed	140	°C	ISO 75-2/A
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index (CTI)	PLC 4		UL 746A
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.75 mm	V-2		
1.5 mm	V-0		



Iupilon™ EGN2030KR
Mitsubishi Engineering-Plastics Corp - Polycarbonate

Processing Information		
Injection	Nominal Value	Unit
Drying Temperature - Hot Air Dryer	120	°C
Drying Time - Hot Air Dryer	4.0 to 8.0	hr
Rear Temperature	280 to 300	°C
Middle Temperature	280 to 300	°C
Front Temperature	280 to 300	°C
Nozzle Temperature	280 to 300	°C
Mold Temperature	80 to 120	°C

