



Mitsubishi Engineering-Plastics Corp.

Iupilon™ GPF2040DF

Mitsubishi Engineering-Plastics Corp - Polycarbonate

General Information			
Product Description			
Reinforced (40%); Flame retard.(Phosphoric acid); Low Warpage; High Flowability			
General			
Filler / Reinforcement	• Glass Fiber, 40% Filler by Weight		
Features	• Flame Retardant	• High Flow	• Low Warpage
Uses	• General Purpose		
ASTM & ISO Properties ¹			
Physical	Nominal Value	Unit	Test Method
Density	1.51	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	10	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	7.9	cm³/10min	ISO 1133
Molding Shrinkage			Internal Method
Across Flow	0.050 to 0.20	%	
Flow	0.050 to 0.20	%	
Water Absorption (Saturation, 23°C)	0.080	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	11000	MPa	ISO 527-1/1
Tensile Stress (Break)	90.0	MPa	ISO 527-2/5
Tensile Strain (Break)	2.0	%	ISO 527-2/5
Flexural Modulus ²	10000	MPa	ISO 178
Flexural Stress ²	150	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	5.0	kJ/m²	ISO 179
Charpy Unnotched Impact Strength (23°C)	23	kJ/m²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	115	°C	ISO 75-2/B
1.8 MPa, Unannealed	110	°C	ISO 75-2/A
CLTE			ISO 11359-2
Flow	2.2E-5	cm/cm/°C	
Transverse	2.9E-5	cm/cm/°C	
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.5 mm)	V-0		UL 94



Iupilon™ GPF2040DF
Mitsubishi Engineering-Plastics Corp - Polycarbonate

Processing Information		
Injection	Nominal Value	Unit
Drying Temperature - Hot Air Dryer	100	°C
Drying Time - Hot Air Dryer	4.0 to 8.0	hr
Rear Temperature	280 to 300	°C
Middle Temperature	280 to 300	°C
Front Temperature	280 to 300	°C
Nozzle Temperature	280 to 300	°C
Mold Temperature	60 to 100	°C

