

Iupilon™ EHR3150

Mitsubishi Engineering-Plastics Corp - Polycarbonate

General Information			
Product Description			
Light Reflection; Flame Retardant, Non-Br & Non-P; High Flowability			
General			
Additive	• Flame Retardant		
Features	• Bromine Free • Flame Retardant	• High Flow • High Reflectivity	• Low (to None) Phosphorus Content
Uses	• Displays • LEDs	• Lighting Applications • Reflectors	
ASTM & ISO Properties ¹			
Physical	Nominal Value	Unit	Test Method
Density	1.30	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	46	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	43	cm ³ /10min	ISO 1133
Molding Shrinkage			Internal Method
Across Flow	0.40 to 0.60	%	
Flow	0.40 to 0.60	%	
Water Absorption (Saturation, 23°C)	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2700	MPa	ISO 527-1/1
Tensile Stress (Yield)	54.0	MPa	ISO 527-2/50
Tensile Strain			ISO 527-2/50
Yield	5.1	%	
Break	13	%	
Flexural Modulus ²	2600	MPa	ISO 178
Flexural Stress ²	89.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	9.0	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	134	°C	ISO 75-2/B
1.8 MPa, Unannealed	117	°C	ISO 75-2/A
CLTE			ISO 11359-2
Flow	6.2E-5	cm/cm/°C	
Transverse	6.3E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	6.0E+15	ohms	IEC 60093
Volume Resistivity	3.0E+16	ohms·cm	IEC 60093



Iupilon™ EHR3150
Mitsubishi Engineering-Plastics Corp - Polycarbonate

Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.5 mm)	V-0		UL 94

Processing Information			
Injection	Nominal Value	Unit	
Drying Temperature - Hot Air Dryer	120	°C	
Drying Time - Hot Air Dryer	4.0 to 8.0	hr	
Rear Temperature	260 to 280	°C	
Middle Temperature	260 to 280	°C	
Front Temperature	260 to 280	°C	
Nozzle Temperature	260 to 280	°C	
Mold Temperature	70 to 100	°C	

