

Iupilon™ GSH2010LR Y082

Mitsubishi Engineering-Plastics Corp - Polycarbonate

General Information			
Product Description			
For Camera, GF Reinforced (10%), Good Surface, Easy Coating			
General			
Filler / Reinforcement	• Glass Fiber, 10% Filler by Weight		
Features	• Good Surface Finish		
Uses	• Camera Applications	• Housings	
ASTM & ISO Properties ¹			
Physical	Nominal Value	Unit	Test Method
Density	1.27	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	17	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	15	cm³/10min	ISO 1133
Molding Shrinkage			Internal Method
Across Flow	0.30 to 0.50	%	
Flow	0.30 to 0.50	%	
Water Absorption (Saturation, 23°C)	0.14	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3300	MPa	ISO 527-1/1
Tensile Stress (Break)	60.0	MPa	ISO 527-2/5
Tensile Strain (Break)	4.6	%	ISO 527-2/5
Flexural Modulus ²	2800	MPa	ISO 178
Flexural Stress ²	105	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	6.0	kJ/m²	ISO 179
Charpy Unnotched Impact Strength (23°C)	70	kJ/m²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	132	°C	ISO 75-2/B
1.8 MPa, Unannealed	126	°C	ISO 75-2/A
CLTE			ISO 11359-2
Flow	5.0E-5	cm/cm/°C	
Transverse	5.9E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index (CTI)	PLC 3		UL 746A
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.40 mm)	HB		UL 94



Iupilon™ GSH2010LR Y082
Mitsubishi Engineering-Plastics Corp - Polycarbonate

Processing Information		
Injection	Nominal Value	Unit
Drying Temperature - Hot Air Dryer	120	°C
Drying Time - Hot Air Dryer	4.0 to 8.0	hr
Rear Temperature	280 to 300	°C
Middle Temperature	280 to 300	°C
Front Temperature	280 to 300	°C
Nozzle Temperature	280 to 300	°C
Mold Temperature	80 to 120	°C

