

Iupilon™ GSH3140R

Mitsubishi Engineering-Plastics Corp - Polycarbonate

General Information			
Product Description			
Glass Fiber Reinforced (High Flowability & High Stiffness), GF40%			
General			
Filler / Reinforcement	• Glass Fiber, 40% Filler by Weight		
Features	• High Flow	• High Rigidity	• High Stiffness
Uses	• General Purpose		
ASTM & ISO Properties ¹			
Physical	Nominal Value	Unit	Test Method
Density	1.50	g/cm³	ISO 1183
Molding Shrinkage			Internal Method
Across Flow	0.20 to 0.40	%	
Flow	0.050 to 0.25	%	
Water Absorption (Saturation, 23°C)	0.080	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	13300	MPa	ISO 527-1/1
Tensile Stress (Break)	155	MPa	ISO 527-2/5
Tensile Strain (Break)	1.8	%	ISO 527-2/5
Flexural Modulus ²	11900	MPa	ISO 178
Flexural Stress ²	230	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	13	kJ/m²	ISO 179
Charpy Unnotched Impact Strength (23°C)	44	kJ/m²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	145	°C	ISO 75-2/B
1.8 MPa, Unannealed	141	°C	ISO 75-2/A
CLTE			ISO 11359-2
Flow	1.4E-5	cm/cm/°C	
Transverse	5.5E-5	cm/cm/°C	
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.40 mm)	HB		UL 94

Processing Information		
Injection	Nominal Value	Unit
Drying Temperature - Hot Air Dryer	120	°C
Drying Time - Hot Air Dryer	4.0 to 8.0	hr
Rear Temperature	280 to 310	°C
Middle Temperature	280 to 310	°C



Iupilon™ GSH3140R
Mitsubishi Engineering-Plastics Corp - Polycarbonate

Injection	Nominal Value	Unit
Front Temperature	280 to 310	°C
Nozzle Temperature	280 to 310	°C
Mold Temperature	80 to 120	°C

