

General Information**Product Description**

Glass Fiber Reinforced; Low anisotropy (Low warpage)

General

Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight	
Features	• Low Anisotropy	• Low Warpage
Uses	• General Purpose	
Appearance	• Black	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.43	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	15	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	14	cm ³ /10min	ISO 1133
Molding Shrinkage			Internal Method
Across Flow	0.20 to 0.40	%	
Flow	0.20 to 0.40	%	
Water Absorption (Saturation, 23°C)	0.090	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	5100	MPa	ISO 527-1/1
Tensile Stress (Break)	51.0	MPa	ISO 527-2/5
Tensile Strain (Break)	1.9	%	ISO 527-2/5
Flexural Modulus ²	4600	MPa	ISO 178
Flexural Stress ²	100	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	3.0	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	27	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	140	°C	ISO 75-2/B
1.8 MPa, Unannealed	134	°C	ISO 75-2/A
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index (CTI)	PLC 4		UL 746A
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.40 mm)	HB		UL 94



Iupilon™ GSH2030R2 K807
Mitsubishi Engineering-Plastics Corp - Polycarbonate

Processing Information		
Injection	Nominal Value	Unit
Drying Temperature - Hot Air Dryer	120	°C
Drying Time - Hot Air Dryer	4.0 to 8.0	hr
Rear Temperature	290 to 310	°C
Middle Temperature	290 to 310	°C
Front Temperature	290 to 310	°C
Nozzle Temperature	290 to 310	°C
Mold Temperature	80 to 120	°C

