

Iupilon™ LGH2410M

Mitsubishi Engineering-Plastics Corp - Polycarbonate

General Information			
Product Description			
Wear Resistance Improved, GF Reinforced (10%), Fluorine resin (20%)			
General			
Filler / Reinforcement	• Glass Fiber, 10% Filler by Weight		
Additive	• PTFE Lubricant: 10%		
Features	• Abrasion Resistant • High Rigidity	• High Stiffness • Wear Resistant	
Uses	• General Purpose		
ASTM & ISO Properties ¹			
Physical	Nominal Value	Unit	Test Method
Density	1.41	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	5.0	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	4.5	cm³/10min	ISO 1133
Molding Shrinkage			Internal Method
Across Flow	0.40 to 0.60	%	
Flow	0.30 to 0.50	%	
Water Absorption (Saturation, 23°C)	0.080	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	4100	MPa	ISO 527-1/1
Tensile Stress (Break)	67.0	MPa	ISO 527-2/5
Tensile Strain (Break)	2.9	%	ISO 527-2/5
Flexural Modulus ²	3700	MPa	ISO 178
Flexural Stress ²	111	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	13	kJ/m²	ISO 179
Charpy Unnotched Impact Strength (23°C)	45	kJ/m²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	148	°C	ISO 75-2/B
1.8 MPa, Unannealed	142	°C	ISO 75-2/A
CLTE			ISO 11359-2
Flow	3.7E-5	cm/cm/°C	
Transverse	6.8E-5	cm/cm/°C	
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.40 mm)	HB		UL 94



Iupilon™ LGH2410M
Mitsubishi Engineering-Plastics Corp - Polycarbonate

Processing Information		
Injection	Nominal Value	Unit
Drying Temperature - Hot Air Dryer	120	°C
Drying Time - Hot Air Dryer	4.0 to 8.0	hr
Rear Temperature	290 to 310	°C
Middle Temperature	290 to 310	°C
Front Temperature	290 to 310	°C
Nozzle Temperature	290 to 310	°C
Mold Temperature	80 to 120	°C

