

Iupilon™ ML200

Mitsubishi Engineering-Plastics Corp - Polycarbonate

General Information			
Product Description			
SAE Approved, Medium Viscosity			
General			
Features	• Medium Viscosity		
Uses	• Automotive Applications		
Automotive Specifications	• SAE Unspecified		
ASTM & ISO Properties ¹			
Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	9.5	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	8.8	cm³/10min	ISO 1133
Molding Shrinkage			Internal Method
Across Flow	0.50 to 0.70	%	
Flow	0.50 to 0.70	%	
Water Absorption (24 hr, 23°C)	0.24	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2500	MPa	ISO 527-1/1
Tensile Stress (Yield)	63.0	MPa	ISO 527-2/50
Tensile Strain			ISO 527-2/50
Yield	6.8	%	
Break	120	%	
Flexural Modulus ²	2300	MPa	ISO 178
Flexural Stress ²	91.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	76	kJ/m²	ISO 179
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	138	°C	ISO 75-2/B
1.8 MPa, Unannealed	125	°C	ISO 75-2/A
CLTE			ISO 11359-2
Flow	6.3E-5	cm/cm/°C	
Transverse	7.3E-5	cm/cm/°C	



Iupilon™ ML200

Mitsubishi Engineering-Plastics Corp - Polycarbonate

Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	4.0E+15	ohms	IEC 60093
Volume Resistivity	3.0E+16	ohms·cm	IEC 60093
Electric Strength			IEC 60243-1
1.00 mm	31	kV/mm	
3.00 mm	17	kV/mm	
Dielectric Constant			IEC 60250
1 MHz	3.10		
100 MHz	3.10		
Dissipation Factor			IEC 60250
1 MHz	9.0E-3		
100 MHz	7.0E-4		

Processing Information			
Injection	Nominal Value	Unit	
Drying Temperature - Hot Air Dryer	120	°C	
Drying Time - Hot Air Dryer	4.0 to 8.0	hr	
Rear Temperature	280 to 300	°C	
Middle Temperature	280 to 300	°C	
Front Temperature	280 to 300	°C	
Nozzle Temperature	280 to 300	°C	
Mold Temperature	70 to 100	°C	

