

XANTAR® RX 2125

Property Data

PC FR

Low Viscosity, Flame Retardant, Molding Release, UV Stabilized

Properties	Typical Data	Unit	Test Method
RHEOLOGICAL PROPERTIES			
Melt volume-flow rate	13	cm³/10min	ISO 1133
Temperature	300	°C	ISO 1133
Load	1.2	kg	ISO 1133
Molding shrinkage (parallel)	0.6	%	ISO 294-4
MECHANICAL PROPERTIES			
Tensile modulus	2300	MPa	ISO 527-1/-2
Yield stress	60	MPa	ISO 527-1/-2
Yield strain	6	%	ISO 527-1/-2
Nominal strain at break	>50	%	ISO 527-1/-2
Flexural modulus	2400	MPa	ISO 178
Flexural strength	90	MPa	ISO 178
Izod notched impact strength (23°C)	70	kJ/m²	ISO 180/4A
Rockwell hardness, M scale	70	-	ISO 2039-2
THERMAL PROPERTIES			
Temp. of deflection under load (1.80 MPa)	130	°C	ISO 75-1/-2
Vicat softening temperature (50°C/h 50N)	145	°C	ISO 306
Coeff. of linear therm. expansion (parallel)	0.65	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.5	mm	IEC 60695-11-10
Burning Behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.75	mm	IEC 60695-11-10
Oxygen index	35	%	ISO 4589-1/-2
Ball pressure temperature	125	°C	IEC 60695-10-2
Glow Wire Flammability Index GWFI	960	°C	IEC 60695-2-12
GWFI (Thickness (1) tested)	1.5	mm	IEC 60695-2-12
Glow Wire Flammability Index GWFI	960	°C	IEC 60695-2-12
GWFI (Thickness (2) tested)	3	mm	IEC 60695-2-12
Glow Wire Ignition Temperature GWIT	825	°C	IEC 60695-2-13
GWIT (Thickness (1) tested)	1.5	mm	IEC 60695-2-13
Glow Wire Ignition Temperature GWIT	850	°C	IEC 60695-2-13
GWIT (Thickness (2) tested)	3	mm	IEC 60695-2-13
ELECTRICAL PROPERTIES			
Relative permittivity (100Hz)	3	-	IEC 60250
Relative permittivity (1 MHz)	2.9	-	IEC 60250
Dissipation factor (100 Hz)	6.6	E-4	IEC 60250
Dissipation factor (1 MHz)	92	E-4	IEC 60250
Volume resistivity	>1E13	Ohm*m	IEC 60093

 Mitsubishi Engineering-Plastics Corporation



XANTAR® RX 2125

Surface resistivity	>1E15	Ohm	IEC 60093
Electric strength	29	kV/mm	IEC 60243-1
Comparative tracking index	225	-	IEC 60112
Comparative tracking index (PLC)	2	class	UL 746A

OTHER PROPERTIES

Water absorption	0.35	%	Sim. to ISO 62
Density	1200	kg/m ³	ISO 1183

MATERIAL SPECIFIC PROPERTIES

Limiting Viscosity Number	46	cm ³ /g	ISO 1628-4
---------------------------	-----------	--------------------	------------

RHEOLOGICAL CALCULATION PROPERTIES

Thermal conductivity of melt	0.24	W/(m K)	-
------------------------------	-------------	---------	---

 Mitsubishi Engineering-Plastics Corporation

