

Iupilon™ MB2212R

Mitsubishi Engineering-Plastics Corp - Polycarbonate + ABS

General Information			
Product Description			
PC/ABS, Low Mold Deposit, High flow			
General			
Features	• High Flow	• Low to No Outgassing	
Uses	• General Purpose		
ASTM & ISO Properties ¹			
Physical	Nominal Value	Unit	Test Method
Density	1.12	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (250°C/2.16 kg)	11	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (250°C/2.16 kg)	10	cm ³ /10min	ISO 1133
Molding Shrinkage			Internal Method
Across Flow	0.40 to 0.60	%	
Flow	0.40 to 0.60	%	
Water Absorption (24 hr, 23°C)	0.12	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2500	MPa	ISO 527-1/1
Tensile Stress (Yield)	55.0	MPa	ISO 527-2/50
Tensile Strain			ISO 527-2/50
Yield	4.4	%	
Break	46	%	
Flexural Modulus ²	2400	MPa	ISO 178
Flexural Stress ²	88.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	70	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	114	°C	ISO 75-2/B
1.8 MPa, Unannealed	96.0	°C	ISO 75-2/A
CLTE			ISO 11359-2
Flow	7.0E-5	cm/cm/°C	
Transverse	7.0E-5	cm/cm/°C	
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.5 mm)	HB		UL 94



Iupilon™ MB2212R
Mitsubishi Engineering-Plastics Corp - Polycarbonate + ABS

Processing Information		
Injection	Nominal Value	Unit
Drying Temperature - Hot Air Dryer	80 to 100	°C
Drying Time - Hot Air Dryer	4.0 to 8.0	hr
Rear Temperature	230 to 270	°C
Middle Temperature	230 to 270	°C
Front Temperature	230 to 270	°C
Nozzle Temperature	230 to 270	°C
Mold Temperature	60 to 90	°C

