

Iupilon™ MB2223R

Mitsubishi Engineering-Plastics Corp - Polycarbonate + ABS

General Information			
Product Description			
PC/ABS, High Impact Strength			
General			
Features	• High Impact Resistance		
Uses	• General Purpose		
ASTM & ISO Properties ¹			
Physical	Nominal Value	Unit	Test Method
Density	1.12	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (250°C/2.16 kg)	5.0	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (250°C/2.16 kg)	5.0	cm³/10min	ISO 1133
Molding Shrinkage			Internal Method
Across Flow	0.50 to 0.70	%	
Flow	0.50 to 0.70	%	
Water Absorption (24 hr, 23°C)	0.12	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2300	MPa	ISO 527-1/1
Tensile Stress (Yield)	51.0	MPa	ISO 527-2/50
Tensile Strain			ISO 527-2/50
Yield	4.7	%	
Break	50	%	
Flexural Modulus ²	2200	MPa	ISO 178
Flexural Stress ²	80.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	60	kJ/m²	ISO 179
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	124	°C	ISO 75-2/B
1.8 MPa, Unannealed	102	°C	ISO 75-2/A
CLTE			ISO 11359-2
Flow	7.0E-5	cm/cm/°C	
Transverse	7.0E-5	cm/cm/°C	
Processing Information			
Injection	Nominal Value	Unit	
Drying Temperature - Hot Air Dryer	90 to 100	°C	
Drying Time - Hot Air Dryer	4.0 to 8.0	hr	
Rear Temperature	240 to 290	°C	



Iupilon™ MB2223R
Mitsubishi Engineering-Plastics Corp - Polycarbonate + ABS

Injection	Nominal Value	Unit
Middle Temperature	240 to 290	°C
Front Temperature	240 to 290	°C
Nozzle Temperature	240 to 290	°C
Mold Temperature	60 to 90	°C

