

Iupilon™ MB4303

Mitsubishi Engineering-Plastics Corp - Polycarbonate + Polyester

General Information			
Product Description			
PC/POLYESTER, Chemical Resistant			
General			
Features	• Chemical Resistant		
Uses	• General Purpose		
ASTM & ISO Properties ¹			
Physical	Nominal Value	Unit	Test Method
Density	1.22	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	20	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	19	cm³/10min	ISO 1133
Molding Shrinkage			Internal Method
Across Flow	0.50 to 0.70	%	
Flow	0.50 to 0.70	%	
Water Absorption (24 hr, 23°C)	0.30	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2500	MPa	ISO 527-1/1
Tensile Stress (Yield)	62.0	MPa	ISO 527-2/50
Tensile Strain			ISO 527-2/50
Yield	5.5	%	
Break	96	%	
Flexural Modulus ²	2400	MPa	ISO 178
Flexural Stress ²	96.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	59	kJ/m²	ISO 179
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	115	°C	ISO 75-2/B
1.8 MPa, Unannealed	97.0	°C	ISO 75-2/A
CLTE			ISO 11359-2
Flow	6.8E-5	cm/cm/°C	
Transverse	6.8E-5	cm/cm/°C	
Processing Information			
Injection	Nominal Value	Unit	
Drying Temperature - Hot Air Dryer	110	°C	
Drying Time - Hot Air Dryer	4.0 to 8.0	hr	
Rear Temperature	270 to 290	°C	



Iupilon™ MB4303
Mitsubishi Engineering-Plastics Corp - Polycarbonate + Polyester

Injection	Nominal Value	Unit
Middle Temperature	270 to 290	°C
Front Temperature	270 to 290	°C
Nozzle Temperature	270 to 290	°C
Mold Temperature	60 to 90	°C

