

Iupital™ FT2010

Mitsubishi Engineering-Plastics Corp - Acetal (POM) Copolymer

General Information

Product Description

Whisker filled

General

Filler / Reinforcement	• Whisker, 10% Filler by Weight
Features	• High Rigidity
Uses	• Automotive Applications • Automotive Electronics • Electrical/Electronic Applications • General Purpose

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.49	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	7.5	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	5.9	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (3.00 mm)	1.7	%	Internal Method
Water Absorption - 60% RH (23°C)	0.23	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	5200	MPa	ISO 527-1/1
Tensile Stress (Break)	73.0	MPa	ISO 527-2/5
Tensile Strain (Break)	5.5	%	ISO 527-2/5
Flexural Modulus ²	4800	MPa	ISO 178
Flexural Stress ²	120	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	5.0	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	90	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	160	°C	ISO 75-2/B
1.8 MPa, Unannealed	140	°C	ISO 75-2/A
Melting Temperature	166	°C	ISO 11357-3
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.8 mm)	HB		UL 94

Processing Information

Injection	Nominal Value	Unit
Drying Temperature - Hot Air Dryer	80	°C
Drying Time - Hot Air Dryer	3.0 to 4.0	hr
Rear Temperature	170	°C
Middle Temperature	180	°C
Front Temperature	190	°C



Iupital™ FT2010

Mitsubishi Engineering-Plastics Corp - Acetal (POM) Copolymer

Injection	Nominal Value	Unit
Nozzle Temperature	180 to 210	°C
Mold Temperature	60 to 100	°C
Injection Pressure	50.0 to 100	MPa
Injection Rate	Moderate	
Screw Speed	80 to 120	rpm

