

Iupital™ FC2020H

Mitsubishi Engineering-Plastics Corp - Acetal (POM) Copolymer

General Information

Product Description

Carbon fiber filled; Rigidity, High

General

Filler / Reinforcement	• Carbon Fiber, 20% Filler by Weight
Features	• High Rigidity
Uses	• Automotive Applications • Automotive Electronics • Electrical/Electronic Applications • General Purpose

ASTM & ISO Properties¹

Physical	Nominal Value	Unit	Test Method
Density	1.46	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	6.0	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	5.4	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (3.00 mm)	0.40	%	Internal Method
Water Absorption - 60% RH (23°C)	0.28	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	17000	MPa	ISO 527-1/1
Tensile Stress (Break)	170	MPa	ISO 527-2/5
Tensile Strain (Break)	2.0	%	ISO 527-2/5
Flexural Modulus ²	16000	MPa	ISO 178
Flexural Stress ²	270	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	7.0	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	50	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	164	°C	ISO 75-2/B
1.8 MPa, Unannealed	162	°C	ISO 75-2/A
Melting Temperature	166	°C	ISO 11357-3
CLTE			ISO 11359-2
Flow	1.5E-5	cm/cm/°C	
Transverse	1.1E-4	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	5.0E+5	ohms	IEC 60093
Volume Resistivity	2.0E+5	ohms·cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.8 mm)	HB		UL 94



Iupital™ FC2020H
Mitsubishi Engineering-Plastics Corp - Acetal (POM) Copolymer

Processing Information		
Injection	Nominal Value	Unit
Drying Temperature - Hot Air Dryer	80	°C
Drying Time - Hot Air Dryer	3.0 to 4.0	hr
Rear Temperature	180	°C
Middle Temperature	190	°C
Front Temperature	200	°C
Nozzle Temperature	180 to 210	°C
Mold Temperature	60 to 100	°C
Injection Pressure	50.0 to 100	MPa
Injection Rate	Moderate	
Screw Speed	80 to 120	rpm

