

PRODUCT DATA SHEET

MetaForm 7200

Description:	MetaForm 7200 is a ultra-high melt strength engineered polyolefin alloy specifically designed to provide an optimum balance of stiffness, cold temperature impact, and low thermal expansion. This material is supplied in Natural, UV stablized, and can be painted via standard TPO conditions, colored, and used with various polyolefin and paint film cap layers		
Applications:	♦ Exterior and Interior parts	♦ Complex structural panels	♦ General pupose thermoforming
Markets:	♦ Automotive	♦ Industrial	♦ Power Motor Sports
	♦ Heavy Truck / Mass transit	♦ Recreational Vehicles	♦ Construction / Agricultural

General Properties	Typical Value ¹	Units	Test Method ²	Conditions
Melt Flow Rate	0.8	g/10 min	ISO 1133	230°C, 2.16 kg
Hardness	65	Shore D	ISO 868	Instantaneous
Specific Gravity	1.10	-	ISO 1183	
Shrink Rate	0.65 – 0.85	%	ISO 294-4	23°C, 24 hrs
Mechanical Properties				
Flexural Modulus	325,000 (2,241)	psi (MPa)	ISO 178	Chord, 2 mm/min
Tensile Strength @ Yield	3,770 (26)	psi (MPa)	ISO 527	50 mm/min
Elongation @ Break	290	%	ISO 527	50 mm/min
Gardner Impact @ 23°C @ 0°C @ -15°C	> 320 (36)	in*lbs (J)	ASTM D5420	Ring in
	> 320 (36)			
	264 (30)			
Multi-Axial Impact @ -15°C Ultimate Energy Failure	27 100% Ductile	J	ASTM D3763	2.2 m/s, < 10% velocity slowdown
Multi-Axial Impact @ -30°C Ultimate Energy Failure	28 50% Ductile	J	ASTM D3763	2.2 m/s, < 10% velocity slowdown
Thermal Properties				
HDT @ 66 psi (0.455 MPa)	240 (116)	°F (°C)	ISO 75	unannealed
@ 264 psi (1.80 MPa)	140 (60)	°F (°C)	ISO 75	unannealed
CLTE	2.6 E-5 (4.7 E-5)	in/in/°F (mm/mm/°C)	ISO 11359	-30°C to 80°C

1. Values given are typical and should not be interpreted as specifications.

2. ISO test methods, along with mold setup conditions conforming to ISO 294-1, 1873-1, & 1873-2 are generally used. However, modifications to ISO may be incorporated in some tests.

9/09

