

DSM Engineering Plastics - Property Data

Yparex® 8305

(E/P)-unfilled

Properties	Typical Data	Unit	Test Method
------------	--------------	------	-------------

RHEOLOGICAL PROPERTIES

Melt flow rate MFR	4.9	g/10min	ISO 1133
MFR test load	2.16	kg	ISO 1133
MFR test temperature	190	°C	ISO 1133

THERMAL PROPERTIES

Melting temperature (10°C/min)	131	°C	ISO 11357-1/-3
--------------------------------	-----	----	----------------


OTHER PROPERTIES

Density	954	kg/m³	ISO 1183
---------	-----	-------	----------

RHEOLOGICAL CALCULATION PROPERTIES

Enthalpy of melting	200	-	ISO 11357-1/-3
---------------------	-----	---	----------------

VISCOSITY-SHEAR RATE



DSM Product

Unlimited. **DSM**

