

Akulon® K222-KGV5

PA6-GF25 FR

25% Glass Reinforced, Flame Retardant (halogen free), Heat Stabilized

Properties	Typical Data	Unit	Test Method
Rheological properties			
	dry / cond		
Molding shrinkage (parallel)	0.6 / *	%	ISO 294-4
Molding shrinkage (normal)	1 / *	%	ISO 294-4
Mechanical properties			
	dry / cond		
Tensile modulus	7300 / -	MPa	ISO 527-1/-2
Stress at break	100 / -	MPa	ISO 527-1/-2
Strain at break	4.3 / -	%	ISO 527-1/-2
Charpy impact strength (+23°C)	45 / -	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	5 / -	kJ/m ²	ISO 179/1eA
Thermal properties			
	dry / cond		
Melting temperature (10°C/min)	220 / *	°C	ISO 11357-1/-3
Burning Behav. at 1.5 mm nom. thickn.	V-2 / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10
Burning Behav. at 3.0 mm nom. thickn.	V-2 / *	class	IEC 60695-11-10
Thickness tested	3 / *	mm	IEC 60695-11-10
Burning Behav. at 0.75 mm nom. thickn.	V-2 / *	class	IEC 60695-11-10
Thickness tested	0.75 / *	mm	IEC 60695-11-10
Glow Wire Flammability Index GWFI	960 / -	°C	IEC 60695-2-12
GWFI (Thickness (1) tested)	1.6 / -	mm	IEC 60695-2-12
Glow Wire Flammability Index GWFI	960 / -	°C	IEC 60695-2-12
GWFI (Thickness (2) tested)	0.75 / -	mm	IEC 60695-2-12



Property Data

Akulon[®] K222-KGV5

Properties	Typical Data	Unit	Test Method
Other properties	dry / cond		
Water absorption	6.1 / *	%	Sim. to ISO 62
Humidity absorption	1.6 / *	%	Sim. to ISO 62
Density	1380 / -	kg/m ³	ISO 1183

