

Akulon® Ultraflow K-FG6

PA6-GF30

30% Glass Reinforced, High Flow

Properties	Typical Data	Unit	Test Method
Rheological properties			
	dry / cond		
Molding shrinkage (parallel)	0.18 / *	%	ISO 294-4
Molding shrinkage (normal)	0.86 / *	%	ISO 294-4
Mechanical properties			
	dry / cond		
Tensile modulus	9350 / 5700	MPa	ISO 527-1/-2
Stress at break	160 / 105	MPa	ISO 527-1/-2
Strain at break	3 / 7	%	ISO 527-1/-2
Flexural modulus	8500 / -	MPa	ISO 178
Flexural strength	235 / -	MPa	ISO 178
Charpy impact strength (+23°C)	85 / 90	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	65 / 65	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	12 / 22	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	10 / 10	kJ/m ²	ISO 179/1eA
Thermal properties			
	dry / cond		
Melting temperature (10°C/min)	220 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	200 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	220 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.2 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.7 / *	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10
Burning Behav. at 3.0 mm nom. thickn.	HB / *	class	IEC 60695-11-10



Akulon® Ultraflow K-FG6

Properties	Typical Data	Unit	Test Method
Thickness tested	3 / *	mm	IEC 60695-11-10
Burning Behav. at 0.75 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	0.75 / *	mm	IEC 60695-11-10
Electrical properties dry / cond			
Relative permittivity (100Hz)	3.5 / 14	-	IEC 62631-2-1
Relative permittivity (1 MHz)	3.3 / 5	-	IEC 62631-2-1
Dissipation factor (100 Hz)	50 / 3000	E-4	IEC 62631-2-1
Dissipation factor (1 MHz)	150 / 1200	E-4	IEC 62631-2-1
Volume resistivity	1E13 / 1E11	Ohm*m	IEC 62631-3-1
Surface resistivity	- / 1E14	Ohm	IEC 62631-3-2
Comparative tracking index	* / 600	V	IEC 60112
Other properties dry / cond			
Water absorption	6 / *	%	Sim. to ISO 62
Humidity absorption	1.8 / *	%	Sim. to ISO 62
Density	1350 / -	kg/m ³	ISO 1183

