

Novamid® ST120 NAT

PA6-I

Impact Modified, Injection Molding

Properties	Typical Data	Unit	Test Method
Rheological properties	dry / cond		
Molding shrinkage [parallel]	1.5 / *	%	Sim. to ISO 294-4
Molding shrinkage [normal]	2 / *	%	Sim. to ISO 294-4
Mechanical properties	dry / cond		
Tensile modulus	1900 / -	MPa	ISO 527-1/-2
Yield stress	45 / -	MPa	ISO 527-1/-2
Yield strain	4.2 / -	%	ISO 527-1/-2
Nominal strain at break	30 / >50	%	ISO 527-1/-2
Flexural modulus	1700 / -	MPa	ISO 178
Flexural strength	66 / -	MPa	ISO 178
Charpy impact strength (+23°C)	N / N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	42 / N	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	15.5 / -	kJ/m ²	ISO 179/1eA
Thermal properties	dry / cond		
Melting temperature (10°C/min)	220 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	53 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	87 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.4 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	1 / *	E-4/°C	ISO 11359-1/-2
Electrical properties	dry / cond		
Relative permittivity (100Hz)	4 / -	-	IEC 62631-2-1



Novamid[®] ST120 NAT

Properties	Typical Data	Unit	Test Method
Relative permittivity (1 MHz)	3 / -	-	IEC 62631-2-1
Dissipation factor (100 Hz)	100 / -	E-4	IEC 62631-2-1
Dissipation factor (1 MHz)	180 / -	E-4	IEC 62631-2-1
Volume resistivity	9E12 / -	Ohm*m	IEC 62631-3-1
Surface resistivity	- / 3E13	Ohm	IEC 62631-3-2
Electric strength	29 / -	kV/mm	IEC 60243-1
Comparative tracking index	600 / -	V	IEC 60112

Other properties

dry / cond

Humidity absorption	2.2 / *	%	Sim. to ISO 62
Density	1070 / -	kg/m ³	ISO 1183

