

Novamid® 2430AH2

PA6/66

High Viscosity, Heat Stabilized, Blow Molding and Extrusion Grade

Properties	Typical Data	Unit	Test Method
Mechanical properties	dry / cond		
Tensile modulus	2500 / -	MPa	ISO 527-1/-2
Yield stress	72 / -	MPa	ISO 527-1/-2
Yield strain	4.1 / -	%	ISO 527-1/-2
Nominal strain at break	>50 / -	%	ISO 527-1/-2
Flexural modulus	2300 / -	MPa	ISO 178
Flexural strength	84 / -	MPa	ISO 178
Charpy impact strength (+23°C)	N / -	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	2.6 / -	kJ/m ²	ISO 179/1eA
Thermal properties	dry / cond		
Melting temperature (10°C/min)	193 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	49 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	76 / *	°C	ISO 75-1/-2
Other properties	dry / cond		
Water absorption	11 / *	%	Sim. to ISO 62
Humidity absorption	2.8 / *	%	Sim. to ISO 62
Density	1120 / -	kg/m ³	ISO 1183
Material specific properties	dry / cond		
Viscosity number	246 / *	cm ³ /g	ISO 307, 1157, 1628
RSV formic acid, 1g/100ml	3.6	-	DSM method



Novamid[®] 2430AH2

Viscosity-shear rate

