

Novamid® 2934A

PA6/66

Monofilament Grade, Highly lubricated, Extrusion Grade, Transparent

Ideal for monofilament extrusion. Super high viscosity. Easier to increase tenacity by stretching.

Properties	Typical Data	Unit	Test Method
Thermal properties			
Melting temperature (10°C/min)	200 / *	°C	ISO 11357-1/-3
Other properties			
Humidity absorption	2.8 / *	%	Sim. to ISO 62
Density	1130 / -	kg/m ³	ISO 1183
Material specific properties			
Viscosity number	278 / *	cm ³ /g	ISO 307, 1157, 1628

