

Novamid® 2420A

PA6/66

Extrusion

Properties	Typical Data	Unit	Test Method
Thermal properties			
Melting temperature (10°C/min)	193 / *	°C	ISO 11357-1/-3
Other properties			
Humidity absorption	3.5 / *	%	Sim. to ISO 62
Density	1140 / -	kg/m ³	ISO 1183
Material specific properties			
Viscosity number	183 / *	cm ³ /g	ISO 307, 1157, 1628



Novamid[®] 2420A

Viscosity-shear rate

