

Novamid® 2020A-8

PA6/66

Extrusion, Medium/High Viscosity, Highly lubricated

Properties	Typical Data	Unit	Test Method
Thermal properties			
Melting temperature (10°C/min)	200 / *	°C	ISO 11357-1/-3
Other properties			
Humidity absorption	2.8 / *	%	Sim. to ISO 62
Density	1130 / -	kg/m ³	ISO 1183
Material specific properties			
Viscosity number	183 / *	cm ³ /g	ISO 307, 1157, 1628



Novamid[®] 2020A-8

Viscosity-shear rate

