

Stanyl® TC502

PA46-GF15

Thermal conductive material

Stanyl® TC502 is thermal conductive high heat polyamide designed for thermal management of electrical components with demanding conductivity levels.

Properties	Typical Data	Unit	Test Method
Rheological properties			
	dry / cond		
Molding shrinkage (parallel)	0.6 / *	%	ISO 294-4
Molding shrinkage (normal)	1.2 / *	%	ISO 294-4
Mechanical properties			
	dry / cond		
Tensile modulus	10000 / 4500	MPa	ISO 527-1/-2
Tensile modulus (120°C)	3300 / -	MPa	ISO 527-1/-2
Tensile modulus (160°C)	2800	MPa	ISO 527-1/-2
Tensile modulus (180°C)	2500	MPa	ISO 527-1/-2
Stress at break	65 / 45	MPa	ISO 527-1/-2
Stress at break (120°C)	33 / -	MPa	ISO 527-1/-2
Stress at break (160°C)	27	MPa	ISO 527-1/-2
Stress at break (180°C)	23	MPa	ISO 527-1/-2
Strain at break	1 / 2	%	ISO 527-1/-2
Strain at break (120°C)	2 / -	%	ISO 527-1/-2
Strain at break (160°C)	2.1	%	ISO 527-1/-2
Strain at break (180°C)	2.1	%	ISO 527-1/-2
Flexural modulus	9400 / 5200	MPa	ISO 178
Flexural modulus (120°C)	3700	MPa	ISO 178
Flexural modulus (160°C)	3200	MPa	ISO 178
Flexural strength	110 / 75	MPa	ISO 178
Flexural strength (120°C)	60	MPa	ISO 178



Property Data

Stanyl[®] TC502

Properties	Typical Data	Unit	Test Method
Flexural strength (160°C)	45	MPa	ISO 178
Charpy impact strength (+23°C)	10 / 13	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	10 / 10	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	4 / 6	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	4 / 4	kJ/m ²	ISO 179/1eA

Thermal properties

dry / cond

Melting temperature (10°C/min)	295 / *	°C	ISO 11357-1/-3
Coeff. of linear therm. expansion (parallel)	0.25 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.35 / *	E-4/°C	ISO 11359-1/-2
Thermal conductivity in plane	14	W/(m K)	ASTM E1461
Thermal conductivity through plane	2.1	W/(m K)	ASTM E1461

Electrical properties

dry / cond

Volume resistivity	10000 / -	Ohm*m	IEC 62631-3-1
--------------------	-----------	-------	---------------

Other properties

dry / cond

Humidity absorption	1.9 / *	%	Sim. to ISO 62
Density	1480 / -	kg/m ³	ISO 1183

